

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

March 16, 2020

Mr. Michael Ting
GALE PACIFIC LIMITED
145 Woodlands Drive
Braeside, Victoria 3195
Australia

Reference: Flammability Test Report
Lab Identification No. 40740
Invoice No. 71960

Dear Mr. Ting:

One (1) sample, identified as **COMMERCIAL NINETYFIVE 340FR – BRUNSWICK GREEN**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

| <u>Specimen Number</u> | <u>Test Results</u> | |
|------------------------|------------------------------------|---------------------------------|
| | <u>Residual Flame</u> (seconds) | <u>Weight Loss</u> (percent) |
| 1 | 0.0 | 0.25 |
| 2 | 0.0 | 0.28 |
| 3 | 0.0 | 0.45 |
| 4 | 0.0 | 0.22 |
| 5 | 0.0 | 0.32 |
| 6 | 0.0 | 6.38 |
| 7 | 0.0 | 0.18 |
| 8 | 0.0 | 1.69 |
| 9 | 0.0 | 2.27 |
| <u>10</u> | <u>0.0</u> | <u>0.87</u> |
| AVG | 0.0 | 1.29 |

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

March 16, 2020

Mr. Michael Ting
GALE PACIFIC LIMITED
145 Woodlands Drive
Braeside, Victoria 3195
Australia

Reference: Flammability Test Report
Lab Identification No. 40740
Invoice No. 71960

Dear Mr. Ting:

One (1) sample, identified as **COMMERCIAL NINETYFIVE 340FR – BRUNSWICK GREEN**, was received and tested in accordance with the National Fire Protection Association No. 701, "Flame Propagation of Textiles and Films, 2019 Edition, (Test 2, Flat Configuration)". The results are as follows:

Test Results

| <u>Specimen Number</u> | <u>After Flame</u> (seconds) | <u>Residual Flame</u> (seconds) | <u>Char Length</u> (inches) |
|------------------------|---------------------------------|------------------------------------|--------------------------------|
| 1 | 0.0 | 0.0 | 10.0 |
| 2 | 0.0 | 0.0 | 11.0 |
| 3 | 0.0 | 0.0 | 9.5 |
| 4 | 0.0 | 0.0 | 12.5 |
| 5 | 0.0 | 0.0 | 12.0 |
| 6 | 0.0 | 0.0 | 11.0 |
| 7 | 0.0 | 0.0 | 11.5 |
| 8 | 0.0 | 0.0 | 9.5 |
| 9 | 0.0 | 0.0 | 9.0 |
| 10 | 0.0 | 0.0 | 10.0 |

The sample submitted **meets** the minimum requirements of the above standard. The length of char on the individual single flat specimens shall not exceed 17.1 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
 WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

March 16, 2020

Mr. Michael Ting
 GALE PACIFIC LIMITED
 145 Woodlands Drive
 Braeside, Victoria 3195
 Australia

Reference: Flammability Test Report
 Lab Identification No. 40740
 Invoice No. 71960

Dear Mr. Ting:

One (1) sample, identified as **COMMERCIAL NINETYFIVE 340FR – BRUNSWICK GREEN**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The results are as follows:

| <u>Specimen Number</u> | <u>Test Results</u> | | <u>Char Length (in)</u> | |
|------------------------|--------------------------|--------------|-------------------------|--------------|
| | <u>After Flame (sec)</u> | | | |
| | <u>Length</u> | <u>Width</u> | <u>Length</u> | <u>Width</u> |
| 1 | 0.0 | 0.0 | 3.1 | 3.6 |
| 2 | 0.0 | 0.0 | 3.2 | 3.1 |
| 3 | 4.0 | 0.0 | 3.8 | 3.3 |
| 4 | 4.0 | 0.0 | 3.6 | 3.5 |
| 5 | <u>0.0</u> | <u>0.0</u> | 3.5 | 3.4 |
| Avg. | 1.6 | 0.0 | | |

The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

