



**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

June 7, 2022

Mr. Tyler Thomas  
GALE PACIFIC  
285 West Central Parkway, Suite 1704  
Altamonte Springs, FL 32714

Reference: Flammability Test Report  
Lab Identification No. 50391  
Invoice No. 81774

Dear Mr. Thomas:

One (1) sample, identified as **GALE Pacific – Commercial Heavy 430FR**, was received and tested in accordance with the National Fire Protection Association No. 701, "Flame Propagation of Textiles and Films, 2019 Edition, (Test 2, Flat Configuration)". The results are as follows:

**Test Results**

<u>Specimen Number</u>	<u>After Flame</u> (seconds)	<u>Residual Flame</u> (seconds)	<u>Char Length</u> (inches)
1	0.0	0.0	9.3
2	0.0	0.0	8.9
3	0.0	0.0	7.7
4	0.0	0.0	8.3
5	0.0	0.0	8.2
6	0.0	0.0	8.7
7	0.0	0.0	8.9
8	0.0	0.0	8.4
9	0.0	0.0	9.5
10	0.0	0.0	9.2

The sample submitted **meets** the minimum requirements of the above standard. The length of char on the individual single flat specimens shall not exceed 17.1 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

Sincerely,

Brian S. Dement

BSD/mr

