

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 7, 2022

Mr. Tyler Thomas
GALE PACIFIC
285 West Central Parkway, Suite 1704
Altamonte Springs, FL 32714

Reference: Flammability Test Report
Lab Identification No. 50391
Invoice No. 81774

Dear Mr. Thomas:

One (1) sample, identified as **GALE Pacific – Commercial Heavy 430FR**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237.1 Flame Resistance, Small Scale Test. The results are as follows:

Test Results

Specimen Number	After Flame (sec)		Char Length (in)	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	3.4	3.8
2	0.0	0.0	3.5	3.4
3	0.0	0.0	3.7	3.6
4	0.0	0.0	3.7	3.4
5	<u>0.0</u>	<u>0.0</u>	3.6	3.3
Avg.	0.0	0.0		


The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 7, 2022

Mr. Tyler Thomas
GALE PACIFIC
285 West Central Parkway, Suite 1704
Altamonte Springs, FL 32714

Reference: Flammability Test Report
Lab Identification No. 50391
Invoice No. 81774

Dear Mr. Thomas:

One (1) sample, identified as **GALE Pacific – Commercial Heavy 430FR**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237.1 Flame Resistance, Small Scale Test. **The sample was tested after 72 hours of leaching.** The results are as follows:

Test Results

Specimen Number	After Flame (sec)		Char Length (in)	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	4.0	3.7
2	0.0	0.0	3.5	3.5
3	0.0	0.0	3.7	3.4
4	0.0	0.0	3.9	3.5
5	<u>0.0</u>	<u>0.0</u>	3.8	3.6
Avg.	0.0	0.0		


The sample submitted, when tested after 72 hours of leaching, **meets** minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 7, 2022

Mr. Tyler Thomas
GALE PACIFIC
285 West Central Parkway, Suite 1704
Altamonte Springs, FL 32714

Reference: Flammability Test Report
Lab Identification No. 50391
Invoice No. 81774

Dear Mr. Thomas:

One (1) sample, identified as **GALE Pacific – Commercial Heavy 430FR**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237.1 Flame Resistance, Small Scale Test. **The sample was tested after 100 hours of accelerated weathering.** The results are as follows:

Test Results

<u>Specimen Number</u>	<u>After Flame (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	3.2	3.1
2	0.0	0.0	3.6	3.7
3	0.0	0.0	3.5	3.7
4	0.0	0.0	3.3	3.8
5	0.0	0.0	3.6	3.6
Avg.	0.0	0.0		

The sample submitted, when tested after 100 hours accelerated weathering, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

Sincerely,

Brian S. Dement

BSD/mr

