



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 7, 2022

Mr. Tyler Thomas
GALE PACIFIC
285 West Central Parkway, Suite 1704
Altamonte Springs, FL 32714

Reference: Flammability Test Report
Lab Identification No. 50391
Invoice No. 81774

Dear Mr. Thomas:

One (1) sample, identified as **GALE Pacific – Commercial Heavy 430FR**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

<u>Test Results</u>		
<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	0.82
2	0.0	3.64
3	0.0	5.49
4	0.0	1.35
5	0.0	1.78
6	0.0	0.37
7	0.0	1.90
8	20.0	15.65
9	0.0	3.54
<u>10</u>	<u>0.0</u>	<u>1.26</u>
AVG	2.0	3.58

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

